

# Bottomkote XXX

## Antifouling



### PRODUCT DESCRIPTION

Bottomkote® XXX is specially formulated for the cost conscious boat owner requiring a good general purpose antifouling paint.

\* Traditional Antifouling Protection for Most Areas

\* Soft Eroding Bottom Paint for Cruising Boats

\* Fast dry allows recoating between the tides

Particularly suited for fiberglass, wood or steel boats with displacement hulls.

### PRODUCT INFORMATION

<b>Colour</b>	Q49-Red , Q69-Blue, Q79-Black
<b>Finish</b>	Matte
<b>Specific Gravity</b>	1.548
<b>Volume Solids</b>	53%
<b>Typical Shelf Life</b>	2 yrs
<b>VOC (As Supplied)</b>	365 g/lt
<b>Unit Size</b>	1 US Quart 1 US Gallon -

### DRYING/OVERCOATING INFORMATION

	Drying		
	10°C (50°F)	23°C (73°F)	35°C (95°F)
Touch Dry	3 hrs	2 hrs	2 hrs
Immersion	12 hrs	12 hrs	12 hrs

Note: Maximum Immersion Times are as follows: 10-35°C/50-95°F - 48 hrs

Overcoated By	Overcoating					
	Substrate Temperature					
	10°C (50°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Max	Min	Min	Max
Bottomkote XXX	12 hrs	-	10 hrs	-	8 hrs	-

### APPLICATION AND USE

<b>Preparation</b>	<p><b>PREVIOUSLY PAINTED SURFACES In Good Condition</b> Remove loose paint by sanding with 80 grade (grit) paper, wipe with Special Thinner 216. <b>In Poor Condition</b> Remove antifouling paint in poor condition with Interstrip Semi-Paste 299E.</p> <p><b>BARE FIBERGLASS</b> Begin by scrubbing well using soap and water and a stiff brush. Rinse with fresh water and allow to dry. Wipe a small area with a clean rag that has been wetted with Fiberglass Solvent Wash 202. While the surface is still wet, wipe with a clean, dry rag. Continue this process until the entire surface has been cleaned. Sand with 80 grade (grit) paper. Remove sanding residue. Wipe with Fiberglass Solvent Wash 202.</p> <p><b>BARE WOOD</b> Sand with 80 grade (grit) paper. Clean with Special Thinner 216. Apply first coat reduced 10% with Special Thinner 216. Fill seams, if necessary, with Seam Compound Brown 30.</p> <p><b>STEEL</b> Contact Interlux® for further details.</p>
<b>Method</b>	At least 2 coats should be applied.
<b>Hints</b>	<p><b>Thinner</b> Bare Wood - Special Thinner 216.</p> <p><b>Cleaner</b> Bare Fiberglass - Fiberglass Solvent Wash 202. Bare Wood - Special Thinner 216. Painted Surfaces - Special Thinner 216.</p> <p><b>Other</b> Spraying of antifouling paints is prohibited in Canada. For application of Bottomkote XXX to underwater metals such as stainless steel, cast iron, lead and bronze, see Interprotect® bulletin. It is best to launch Bottomkote XXX within 24 hours of painting.</p>
<b>Some Important Points</b>	Do not use above the waterline. Product temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Ambient temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Substrate temperature should be minimum 10°C/50°F and maximum 35°C/95°F.
<b>Compatibility/Substrates</b>	Apply to clean, dry, properly prepared surfaces only. Bottomkote XXX can be applied to most popular antifouling paints as long as the old coating has been aged, is tightly adhered and is in sound condition. Do not apply Bottomkote XXX over aluminum. Do not apply Bottomkote XXX over graphite antifouling.
<b>Number of Coats</b>	2 Bare Wood: 3 coats (first thinned)

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

# Bottomkote XXX Antifouling



---

<b>Coverage</b>	(Theoretical) - 10.318 m <sup>2</sup> /lt by brush
<b>Recommended DFT per coat</b>	50 microns dry
<b>Application Methods</b>	Brush, Roller

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<p><b>TRANSPORTATION:</b> Bottomkote XXX should be kept in securely closed containers during transport and storage.</p> <p><b>STORAGE:</b> Exposure to air and extremes of temperature should be avoided. For the full shelf life of Bottomkote XXX to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.</p>
<b>Safety</b>	<p>DISPOSAL: Container Disposal: Triple Rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill or by other procedures approved by state or local authorities. Pesticide Disposal: Open dumping is prohibited. Pesticide, spray mixture or rinsate that cannot be used or chemically reprocessed should be disposed of according to procedures approved by Federal, state, or local disposal authorities. GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p>Contains biocides. Antifouling should only be wet sanded. Never dry sand or burn-off old antifouling. Spraying of antifouling paints is prohibited in Canada.</p>
<b>IMPORTANT NOTES</b>	<p><i>The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC., including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC. cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND/OR MERCHANTABILITY ARE EXCEEDED. International Paint Inc. SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase of this product, the buyer agrees that the sole exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC. option.</i></p>

---

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.